



# BELZONA® 4141 (MAGMA-BUILD)

## INSTRUCTIONS FOR USE

### 1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

Any surface to which **Belzona® 4141** is to be applied must be clean, firm and dry. Wash old concrete down with detergent to remove oil, grease and dust. Use clean water to wash away the detergent.

Remove all paint, tar and any other coatings.

Allow new concrete to cure for a minimum of 28 days or until the moisture content is below 6% using a Protimeter.

Wire brush, or mechanically abrade the surface to remove loose material.

Horizontal concrete surfaces and new concrete will show the phenomenon of surface laitence and this must be removed by mechanical scarification.

Abrade metallic surfaces to remove loose rust and flaking paint and then roughen by blasting, grinding or other suitable means to achieve a rough bright metal surface. Vacuum up any loose dust produced by surface preparation techniques.

Treat any surfaces to which **Belzona® 4141** should not adhere with **Belzona® 9411** (Release Agent) and leave for 15 - 20 minutes to dry before proceeding; seal porous surfaces to be treated with **Belzona® 9411** first, with a suitable lacquer, e.g. shellac or cellulose enamel.

### 2. CONDITIONING

Add the entire contents of **Belzona® 4911** (Magma TX Conditioner) Solidifier to **Belzona® 4911** Base and stir thoroughly until completely mixed. Immediately brush all of this conditioner onto the surface to be treated with **Belzona® 4141**, with a stiff bristled brush, not exceeding an area of 12 sq.ft. (1.1 m<sup>2</sup>).

#### NOTES:

- For mixing small quantities of **Belzona® 4911** use:  
2 Parts Base : 1 Part Solidifier by Volume
- Conditioning and overcoating must be completed within the times shown opposite:

Ambient Temperature	Usable life after mixing	Minimum overcoating time	Maximum overcoating time*
41°F/ 5°C	230 mins	Application can commence as soon as conditioning has been completed.	6 hours
50°F/10°C	105 mins		6 hours
59°F/15°C	55 mins		6 hours
68°F/20°C	45 mins		6 hours
77°F/25°C	32 mins		6 hours

\* If the maximum overcoating time for the **Belzona® 4911** is exceeded, then the cured surface should be abraded and fresh **Belzona® 4911** applied.

### 3. COMBINING THE REACTIVE COMPONENTS

Mixing may be carried out in the large bucket supplied but due to the bulk and stiffness of the mixed materials, it is essential that a mechanical mixer is used to ensure complete mixing.

Add approximately half the Base component and all of the Solidifier component to the mixing container and start the mixer.

Once initial incorporation has been achieved, slowly add the remainder of the Base material and mix together thoroughly for approximately 5 minutes, or until an even color and consistency are achieved. During this time periodically stop the mixer and withdraw the mixing paddle and scrape clean before continuing mixing.

#### NOTES:

##### 1. WORKING LIFE

From the commencement of mixing, **Belzona® 4141** must be used within the times shown below:

Temperature	Use all material within
50°F/10°C	3 hours
59°F/15°C	1½ hour
68°F/20°C	1 hour
77°F/25°C	45 mins

To extend the working life of mixed **Belzona® 4141** spread the material out on a sheet of polyethylene and keep it in a cool place out of direct sunlight.

## 2. MIXING SMALL QUANTITIES

for mixing small quantities of **Belzona® 4141**, use:  
7 parts Base to 1 part Solidifier by weight, or  
10 parts Base to 1 part Solidifier by volume.

For convenience, measuring vessels of 1 litre and 100 cm<sup>3</sup> capacity are supplied with the product. The Base component should be packed down tightly into the orange 1 litre container when measuring out.

## 3. VOLUME CAPACITY OF MIXED BELZONA® 4141

671 cu.ins. (11,000 cm<sup>3</sup>) per 8.0 kg unit.

## 4. APPLYING BELZONA® 4141

The mixed **Belzona® 4141** is best applied by gloved hand, forcing the material firmly into the areas to be rebuilt leaving the **Belzona® 4141** proud of the surrounding area.

It can then be finished with a steel float or similar tool. Best results are obtained by continuously wetting the float or tool with clean water.

### NOTES:

#### 1. APPLICATION LIMITS

**Belzona® 4141** can be applied when the temperature is anywhere between 41°F (5°C) and 77°F (25°C).

#### 2. DAMP SURFACES

**Belzona® 4141** can be applied to damp surfaces but its adhesion will be approximately 75% of that obtained on a dry surface.

#### 3. APPLYING ADDITIONAL LAYERS OF BELZONA® 4141

Where this is required it should be done as soon as the first layer is firm enough to accept the second layer and within the maximum overcoating time of 6 hours.

After this time the surface of the **Belzona® 4141** must be abraded before further application.

In all cases the surface must be conditioned with **Belzona® 4911** (see Section 2) before applying further **Belzona® 4141**.

## 4. COLORING

**Belzona® 4141** is supplied in cement gray and stone colors but it can be tinted as required by initially mixing powder type concrete coloring additives such as Cementone or Trumix Color Pack with the Base Component. As a guide, an addition of 0.5-1.0% by weight of colorant is sufficient to give a strong color with the lighter stone colored material being easier to tint.

## 5. CLEANING

Mixing tools should be cleaned immediately after use with **Belzona® 9111** or any other effective solvent eg. MEK. Brushes, injection guns, spray equipment and any other application tools should be cleaned using a suitable solvent such as **Belzona® 9121**, MEK, acetone or cellulose thinners.

## 5. COMPLETION OF THE MOLECULAR REACTION

Allow **Belzona® 4141** to solidify for the following times before subjecting it to the conditions indicated:

Temperature	41°F (5°C)	59°F (15°C)	77°F (25°C)
Dimensionally stable	20 hours	9 hours	5 hours
Full mechanical strength	7 days	2 days	1 day
Full chemical resistance	24 days	12 days	7 days

## HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Material Safety Data Sheets.

All descriptions are based on the results of long term tests carried out in our laboratories and are believed to be true and accurate. No condition or warranty is given covering the results from the use of our products in any particular case, whether the purpose is disclosed or not, and we cannot accept liability if the desired results are not obtained.

Copyright © 2002 by Belzona International Limited. All rights reserved. Certain portions of this work copyright © 1980-2001 by Belzona International Limited. No part of this work covered by the copyrights hereon may be reproduced or used in any form or by any means - graphic, electronic or mechanical including photocopying, recording, taping or information storage and retrieval systems - without written permission of the publisher. Belzona® is a registered trademark

## Belzona® 4141 - Instructions For Use - (Page 2)

Printed in England Publication No. 53-7-01

**Belzona Polymerics Ltd.**,  
Claro Road,  
Harrogate, HG1 4AY, England.  
Tel: +44 (0) 1423 567641  
Fax: +44 (0) 1423 505967  
E-Mail: belzona@belzona.co.uk

**Belzona Inc.**,  
2000 N.W. 88 Court,  
Miami, Florida 33172, U.S.A.  
Tel: +1 (305) 594 4994  
Fax: +1 (305) 599 1140  
E-Mail: belzona@belzona.com



BS EN ISO 9002 : 1994  
Certificate No. Q09335



[www.belzona.com](http://www.belzona.com)